



# RASOCAL

READY MIXED SMOOTH-FINISH LIME PLASTER

**INFORMATION SHEET N° 2350** 

#### COMPOSITION

Lime Putty Compound

## **PRODUCT PROPERTIES**

Pure Lime Putty, selected, free of impurities Heat resistent



## FIELD OF USE

Repairs and restoration work. As a fine smooth finish for plaster and decoration. For salt-and-pepper effects on fine finish lime plaster.

#### SUITABLE SUBSTRATES/BACKGROUNDS - INTERIOR OR EXTERIOR

Prepared plaster surfaces New finishing plaster/render

## METHOD OF APPLICATION

Dampen the substrate with water if excessively dry Ensure that the surface areas to be treated are free of dust, oil, grease and contaminating substances Avoid applying at temperatures of less than +5°C and more than +35°C Apply two coats with a trowel or float to level off the surface To be finished with a float or spatula, moistening with water if necessary

with approx. 3 hours of application - less in high temperatures

### MAIN PROPERTIES

<ul> <li>Specific weight</li> </ul>	1360g/litre
-------------------------------------	-------------

- PH over 12
- Colour white no alteration
- Alkali-resistance
- Hardening
  - Average theoretical yield 50m<sup>2</sup> per 22kg pack
- Average consumptionkg 0.400 / m<sup>2</sup>

## PACKAGING AND STORAGE



22kg plastic buckets Store in a cool, dry place, away from frost and direct sunlight

# WARNING

Eve and skin-irritant In the event of eye contact, wash immediately and thoroughly with water, and see a doctor if discomfort is continuous Keep the packaging out of the reach of children



Our advice and information are given in good faith and depending on the latest developments of our products. We guarantee the consistent quality of our products, but do not accept any liability concerning their application. In any case, we do recommend to consider the type of substrate and the climatic conditions before applying our products or to apply a test surface in order to analyse the suitability of the product for the given substrate.

In case of doubt regarding the substrate, consult our technical service department.



TEL: +32 3 880 73 73 FAX: +32 3 880 73 70 WWW.ARTECONSTRUCTO.BE INFO@ARTECONSTRUCTO.BE