

UNILIT 30 (TD13 S) stabilising mortar

OUTLINE SPECIFICATION
plastering
rendering
masonry and pointing
tadelakt

PRODUCT DESCRIPTION

UNILIT 30 is a traditional, dry premixed mineral stabilising mortar based on natural hydraulic lime as the binder and appropriate well-graded aggregates.

UNILIT 30 is characterised by a slow but strong bonding, a high plasticity, a low content of soluble salts and an excellent water vapour permeability. The natural hydraulic lime mortar is inherently stable and designed to reduce problems of micro cracks along with premature drying out. **UNILIT 30** is perfectly water repellent and, hence, performs perfectly where rising damp and capillary action is prevalent. Furthermore, the natural pore structure of hydraulic lime gives **UNILIT 30** a high resistance against salt crystallisation.

The natural hydraulic lime binder, used to prepare the preblend, conforms to the European Standard EN 495-1, NHL 5 for building limes. The mortar **UNILIT 30** conforms to the European Standard UNI EN 998-1.

APPLICATION AREA

UNILIT 30 is applied wherever, both from internally and externally, an important exposure to moisture and/or soluble salts is present. By the application of the stabilising mortar **UNILIT 30** the humidity present in the structure is separated from the finishing layer to be applied, while its optimum vapour permeability allows humidity present in the wall to be able to rapidly migrate from the structure beneath. The separation of the finishing layer from the humidity present in the structure stops the transport of soluble salts as well, which crystallise within the stabilising mortar layer.

UNILIT 30 can be applied to damp walls of buildings and cellars, as a plinth or pointing, both internally and externally, for the protection of the structure against the effects of rising damp or as a protection of the background within humid environments, such as showers, saunas and hammams. Therefore, **UNILIT 30** is essential within the realisation of a tadelakt finish.

UNILIT 30 can be applied as well for the stabilisation of salt loaden backgrounds.

APPLICATION

Prior to application, the substrate must be cleaned and freed of all traces of oil and grease. The substrate benefits from being slightly dampened. Saturation of the substrate is not recommended, as this will influence negatively impact upon the bond of the hydraulic lime mortar to the substrate as well as the aesthetic appearance.

The mortar is mixed with clean water at a ratio of 5 to 6 litres of water to a bag of 30 kg ready mixed natural hydraulic lime powder. Mixing is undertaken with a slow speed electric paddle for a period of 4 to 5 minutes. A creamy workable mortar is obtained, which has approximately 2 hours of open time.

The mortar is applied either manually or by mechanical means at a nominal thickness of 15 to 20 mm. A drying period of 3 to 4 days must be respected. If a finishing layer is applied to the **UNILIT 30** after 1 week a bonding layer of **UNILIT 15/P1** or **UNILIT 15/P2** is required.

The mortars must not be applied at temperatures below +5°C nor when a risk of frost exists. They should never be applied on to a frozen surface or in the case of thick fog. In hot, windy and dry conditions measures should be taken to prevent accelerated drying out of the freshly applied mortars. Applied mortars must be protected from frost and direct sunlight for 48 to 72 hours after their application.

REMARKS

In case of doubt regarding the substrate (e.g. treatment with an impregnating product such as silicones or comparable), consult our technical service department.

The maximum storage time is 6 months, if stored in the original, hermetically closed packing in a suitable environment. The material must be stored dry and frost free above ground. Protect the material from heat sources.

TECHNICAL DATA

Granular sizing	max. 4 mm
Bulk density	1750 - 1850 kg/m ³
Compressive strength (EN 1015-11)	
class CS III (3.5 N/mm ² ≤ f _c ≤ 7.5 N/mm ²)	
Modulus of elasticity	ca. 6130 N/mm ²
Vapour diffusion resistance (μ)	10
Capillar water absorption (EN 1015-18)	
class W2 (c ≤ 0.05 kg/m ² /min ^{1/2})	
pH	
fresh mortar paste	> 10.5
hardened mortar	~ 7
Fire resistance classification (EN 13501)	A1
Proportion water/preblend	0.18 l/kg
Mixing time	4 to 5 minutes
Consumption	15 - 18 kg/m ² /cm
Maximum layer thickness	20 mm
Packing	powder in bags of 30 kg
Colour	beige

This sheet cancel and replace all previous sheets.
Our advice and information are given in good faith and depending on the latest developments of our products. We guarantee the consistent quality of our products, but do not accept any liability concerning their application. In any case, we do recommend to consider the type of substrate and the climatic conditions before applying our products or to apply a test surface in order to analyse the suitability of the product for the given substrate.